



APTEK LABORATORIES, INC.

ISO 9001 / AS9100 Certified

28570 Livingston Avenue, Valencia, CA 91355-4171 • (661) 257-1677 FAX (661) 257-8939

TECHNICAL DATA & INFORMATION

APTEK® 2503R-A/B

Premeasured conformal coating repair kit

PRODUCT DESCRIPTION

APTEK 2503R-A/B is an unfilled, two component, electrically insulating, transparent, flexible urethane coating system designed for the encapsulation and protection of electrical/electronic components mounted on printed circuit boards.

KEY FEATURES AND BENEFITS

- Ideal for repair—ready-to-use—no weighing or blending equipment needed
- Fully compatible with APTEK 2503-A/B conformal coating as well as other commercially available urethane coatings
- Excellent reversion resistance for good physical stability under high heat and humidity environments
- Tg BELOW -70°C for excellent low temperature cycling, storage and performance
- Excellent substrate adhesion; superior to silicones
- Exceeds NASA outgassing requirements for high vacuum environments
- Fluoresces under black-light (UV) to facilitate QC inspection of coating coverage of repaired components/substrates
- Non-TDI based for safety

HANDLING INFORMATION

Work life, after mix @ 25°C, 15 gm mass, hour >3

APTEK 2503R-A/B kits must be used in their entirety. See mixing instructions below.

MIXING

Pour entire contents of Part B (smaller vial) into larger Part A vial. **DO NOT** shake Part B out of vial; let drain for 10 seconds. Replace cap on Part A vial and shake vigorously for approximately 15 seconds. Allow mixture to set for 3-5 minutes for bubbles to be eliminated. Mixture is now ready to use.

CURE SCHEDULE

8 hrs. @ 80°C*

or

5 hrs. @ 100°C*

or

2 hrs. @ 125°C*

- DISCLAIMER NOTICE -

All statements, technical data, and recommendations expressed herein are based on tests believed to be reliable and accurate. However, APTEK LABORATORIES, INC. gives no warranty, expressed or implied, regarding the accuracy of this information. It is intended that the buyer and user of these products shall determine the suitability of the information provided for his specific application, and is responsible for its selection.

APTEK LABORATORIES, INC. shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or misuse of these products, or of the information given in these data bulletins. Purchasers assume all risk and liability whatsoever in connection with the use of these products and this information.

* It is recommended that coated substrates air dry 60 minutes at RT prior to heat cure to allow solvent evaporation and minimize chance for bubble formation during heat cure.

Note: As typical with urethane systems, a relaxation/stabilization period of 2-4 days after cure is required before testing, service, or use.

TYPICAL PROPERTIES

(values not to be used for specification purposes)

<u>CHARACTERISTICS</u>	<u>APTEK 2503R-A</u>	<u>APTEK 2503R-B</u>	<u>TEST METHOD</u>
Flash point, °C	10	>150	ASTM D-92
Shelf life @ 25°C, months in factory sealed containers	6	6	

<u>CURED PHYSICAL PROPERTIES:</u>	<u>APTEK 2503R-A/B</u>	<u>TEST METHOD</u>
Hardness, Durometer A	88	ASTM D-2240
Tensile strength, psi	2800	ASTM D-412
Elongation, %	525	ASTM D-412
Glass transition temp., °C	-74	ASTM E-831
Thermal coefficient of expansion, in/in/°C	180 x 10 ⁻⁶	ASTM E-831
Outgassing @ 10 ⁻⁶ Torr		
TML, %	0.187	ASTM E-595
CVCM, %	0.002	ASTM E-595
Evidence of haze	none	

SAFETY AND FIRST AID

APTEK 2503R-A is an unfilled polyol resin containing solvent and is thus considered a flammable liquid and should be treated with caution. Avoid storage temperatures above 25°C and keep away from flame, sparks, or other sources of ignition. Use in well-ventilated area and avoid breathing vapors. In case of eye contact, flush with fresh clean water for at least 15 minutes; for skin contact, wash thoroughly with soap and water. If swallowed, drink at least one pint of water and call a physician. Refer to Material Safety Data Sheet for more details.

APTEK 2503R-B is an organic isocyanate and is safe to handle when used properly. May cause eye and skin irritation with direct contact. Inhalation of vapors may result in breathlessness, coughing, chest discomfort, and irritation of mucous membranes. Avoid skin and eye contact and use in well-ventilated, hooded area. In case of eye contact, flush profusely with fresh clean water and contact physician. For skin contact, wash thoroughly with soap and water. If inhaled, move subject to fresh air and provide fresh water to drink. If swallowed, dilute with at least one pint of water and contact physician immediately. Refer to Material Safety Data Sheet for more details.

FOR INDUSTRIAL USE ONLY

Revised: 08/08/11 - di

APTEK® is a registered trademark of Aptek Laboratories, Inc