



APTEK LABORATORIES, INC.

ISO 9001 / AS9100 Certified

28570 Livingston Avenue, Valencia, CA 91355-4171 • (661) 257-1677 FAX (661) 257-8939

TECHNICAL DATA & INFORMATION

APTEK® 2711

Inorganic, thermally radiative, ESD paint

PRODUCT DESCRIPTION

APTEK 2711 is a white, rigid, mineral oxide filled, one component, room temperature curing, inorganic coating/paint designed for very high temperature space applications. **APTEK 2711** was developed for use as thermally conductive coating where excellent resistance to intense UV light exposure is required.

KEY FEATURES AND BENEFITS

- JPL field-approved formulation; already on hardware in space
- Inorganic silicate binder provide coating with a service temperature $\geq 700^{\circ}\text{C}$ (1300°F). This coating somewhat brittle and should only be used on rigid substrates
- Passes NASA outgassing per ASTM-E 595
- Inherently has sufficient surface conductivity for ESD applications on conductive surfaces
- Water-based formulation for safety. Formulated to sprayable viscosity for convenience

HANDLING INFORMATION

1. **APTEK 2711** is a one component, ready-to-spray system, however, it may be thinned up to an additional 25% by volume with distilled water.
2. Filler will settle upon storage. Homogenize prior to use by vigorously shaking the sealed container. Ceramic stirrer beads are embedded in the filler layer to aid in re-dispersion.
3. Once uniform, pour freshly agitated **APTEK 2711** into spray gun reservoir. For best results, keep mixture in spray reservoir stirred or shaken during spraying procedure.
4. SURFACE PREPARATION
 - a. Substrate surface to be sprayed should be clean and dry and free from silicone, mineral, petroleum oils/greases, etc.
 - b. It is recommended that substrates be scrubbed with an abrasive cleaner. Then rinse with distilled water until a uniform "sheet" of water film appears on surface. Rinse in clean, anhydrous IPA, and allow to air dry for 15 minutes. Then bake for 15 minutes @ 65°C in an air circulating oven.
5. SURFACE PRIMING
 - a. Priming of some surfaces may not be required. User to determine if needed.
 - b. Specimens should be cleaned/prepared by above procedure (or equivalent) within 2 hours prior to priming.
 - c. The best primer to use is **APTEK 2711** itself. Apply a thin coat (≤ 0.5 mil) by rubbing **APTEK 2711** into the cleaned surface using a clean, dry, lint-free cloth.

- DISCLAIMER NOTICE -

All statements, technical data, and recommendations expressed herein are based on tests believed to be reliable and accurate. However, APTEK LABORATORIES, INC. gives no warranty, expressed or implied, regarding the accuracy of this information. It is intended that the buyer and user of these products shall determine the suitability of the information provided for his specific application, and is responsible for its selection.

APTEK LABORATORIES, INC. shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or misuse of these products, or of the information given in these data bulletins. Purchasers assume all risk and liability whatsoever in connection with the use of these products and this information.

- d. This rubbed in coating shall air dry until the water has evaporated and surface looks dry. This should occur within a few minutes but not more than 15 minutes.

6. PAINT APPLICATION

- Use dry nitrogen, dry air, or argon as pneumatic spraying medium
- Spray multiple thin coats to freshly primed surfaces until a total thickness of 2-4 mils is achieved.
- A uniform thickness draw-down blade applicator may be used to screed down the coating in lieu of a spray application for small specimen sizes.
- Estimated surface area coverage per quart is 25-30 sq. ft. at 3-4 mils cured thickness.

CURE SCHEDULE

7 days at @ RT @40-60% RH

Cure schedule is a guideline. User to determine actual cure for application. Note that lower % RH will speed up cure rate and higher % RH will tend to slow cure rate.

TYPICAL PROPERTIES

(values not to be used for specification purposes)

<u>CHARACTERISTICS</u>	<u>2711</u>	<u>TEST METHOD</u>
Color	white to pale yellow	Visual
Specific Gravity	1.77	ASTM D-1475
Viscosity @ 25°C,cps	200	ASTM-D-1824
Flash point, °C	N/A	
Shelf life, months @25°C in factory sealed containers	6	
<u>CURED PHYSICAL PROPERTIES</u>	<u>2711</u>	<u>TEST METHOD</u>
Solar absorption, α_s vs thickness	α_s /mils 0.20/2 0.19/3 0.18/4	SCGPS 10008
Outgassing @ 10^{-6} torr, TML, % CVCN, %	0.50 0.02	ASTM E-595
Surface resistivity, on conductive surfaces ohms/sq @ 10^{-6} torr, ohms/sq.	10^6 to 10^9 10^6 to 10^9	ETS-872A
Infrared emittance	≥ 0.88	SCGPS 10008

SAFETY AND FIRST AID

APTEK 2711 is a water-based, mineral filler, low viscosity coating which is safe to handle when used properly. Store the coating at 15-30°C in original factory sealed containers. In case of eye contact, flush with fresh clean water for at least 15 minutes; for skin contact wash thoroughly with soap and water. If swallowed, drink at least one pint of water and call a physician. Refer to MSDS for more details.

Issued: 10-13-1998 Revised: 10-16-09 - di

APTEK® is a registered trademark of Aptek Laboratories, Inc.