



APTEK LABORATORIES, INC.

ISO 9001 / AS9100 Certified

28570 Livingston Avenue, Valencia, CA 91355-4171 • (661) 257-1677 FAX (661) 257-8939

TECHNICAL DATA & INFORMATION

APTEK® 2712-A/B

- Very low stress Silicone Adhesive
- -110°C to 260°C operating range
- Low outgassing/space grade

PRODUCT DESCRIPTION

APTEK 2712-A/B is a two component, white, very soft, thixotropic, electrically insulative, silicone adhesive displaying excellent flow temperature flexibility and unusually high physical strength properties.

APTEK 2712-A/B has been designed to fully cure at room temperature and can be accelerated with a brief low temperature cure. This 100% solids system has been manufactured with highly pure resins to minimize the occurrence of ionic contamination without outgassing during cure or service.

KEY FEATURES AND BENEFITS

- Very flexible/low modulus over wide temperature range to absorb stress build-up during thermal cycling
- Convenient 1/1 PBW or PBV mix ratio for easy handling-ideal for cartridge dispensers/repair kits
- Very good adhesion to various substrates when used in conjunction with G.E. SS4155 primer or Dow Corning's 1200 primer.

HANDLING INFORMATION

Mix ratio, PBW or PBV 100 (2712-A)/100 (2712-B)

Work Life, @ 25°C, 10 gm mass, minutes 30

Handling Notes

- Silicone resins and primers are moisture sensitive, therefore, blanket containers of any unused portions with Argon or dry nitrogen prior to resealing.
- Prior to application of adhesive, clean part(s) to be bonded with a lint free cloth and MEK or other suitable degreaser. Then wipe with isopropyl alcohol and allow to dry.
- Priming Procedure:
 - Apply primer to clean, dry surface by brushing, wiping with a lint free cloth, or dipping. Spraying may sometimes produce erratic results and is not recommended.

- DISCLAIMER NOTICE -

All statements, technical data, and recommendations expressed herein are based on tests believed to be reliable and accurate. However, APTEK LABORATORIES, INC. gives no warranty, expressed or implied, regarding the accuracy of this information. It is intended that the buyer and user of these products shall determine the suitability of the information provided for his specific application, and is responsible for its selection.

APTEK LABORATORIES, INC. shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or misuse of these products, or of the information given in these data bulletins. Purchasers assume all risk and liability whatsoever in connection with the use of these products and this information.

- Only apply a very thin coat of primer approximately 0.015mm (0.5mil). Excess primer will actually reduce adhesion.
- Allow primer to dry for 90 minutes to 2 hours at 25°C and 45-75% RH prior to application of fresh adhesive mixture. Longer drying times may be required when RH is below 40%.
 - NOTE: We have found that mixing fresh GE SS4155 primer with anhydrous isopropyl alcohol at 1/1 PBW or PBV has demonstrated improved adhesion.
- Primer may be left to dry for up to 12 hours before application of the sealant without loss of bonding effects. However, the primed surface must be covered to prevent dirt or contaminant pick-up.

COMPATIBILITY:

Certain materials, chemicals, curing agents and plasticizers can inhibit the cure of silicone encapsulants and adhesives. Most notable of these include:

- Organotin and other organometallic compounds
- Silicone rubber containing organotin catalyst
- Sulfur, polysulfides, polysulfones or other sulfur-containing materials
- Amines, urethanes or amine-containing materials
- Unsaturated hydrocarbon plasticizers
- Some solder flux residues
- Latex rubber gloves

MIXING

Bulk handling

Weigh 100 parts of 2712 Part A into a clean, dry, glass, or metal, container and then add 100 parts of 2712 Part B. DO NOT MACHINE MIX-hand stir with glass or metal stirrer until complete and thorough blending is achieved, care should be taken to avoid any source of moisture contamination or air entrapment during mix.

Note: For best results and void-free bond line, vacuum mixture @ less than 10 mm Hg for 5 minutes minimum.

Dual cartridge/dispenser kits

- Hold cartridge firmly and upright.
- Twist protective cap counterclockwise 90° and pull protective cap off, exposing the adhesive ports.
- Insert flanged base of mixing tube over the exposed adhesive ports perpendicular to the cartridge bracket. Note this is keyed and will only fit in one orientation.
- Rotate turquoise collar clockwise 90°. Ensure that mix tip is securely attached.
- Hold gray handles of ratchet gun, with up arrow facing you.
- While lifting and holding up silver lever with thumb, pull back black plunger fully, until it stops.
- Insert the cartridge into slot in front of gun.
- Continue to apply pressure to trigger to dispense adhesive through the tube.
- Allow one inch of adhesive to extrude before applying to bonding surface.

- Cut back tip of tube to adjust bead size.
- If using a luer lock adaptor, cut off the first two segments from the mix tip. Thread the luer lock adaptor on the third segment. Attach appropriate compatible luer lock tip.
- To remove plunger from spent cartridge hold up silver lever and pull back black plunger fully; then cartridge can be removed from gun.

CURE SCHEDULE

5-7 days @ RT
or
1 hour @ 65°C
or
30 mins @ 100°C
or
15 mins. @ 150°C

NOTES:

1. Above cure schedules are guidelines and user should determine proper cure depending on achievement of the application requirements.
2. For RT cure only:
 - Some surface tackiness may be evident up to 48 hours. However, adhesive will be firmly gelled.
 - Adhesive will continue to develop full strength in 5-7 days.
3. For RT setup followed by heat post cure:
 - User to determine how long at RT is required to achieve sufficient strength needed for specific application prior to heat post cure. It is recommended that the full heat cure is used as indicated above.

TYPICAL PROPERTIES

(values not to be used for specification purposes)

<u>CHARACTERISTICS</u>	<u>2712-A</u>	<u>2712-B</u>	<u>TEST METHOD</u>
Color	White	Translucent	Visual
Specific Gravity	1.15	1.15	ASTM D-1475
Viscosity @ 25°C	smooth, thixotropic paste	smooth, thixotropic paste	Visual
Flash point, °C	>150°C	>150°C	ASTM D-92
Shelf life @ 5°C or below in factory Sealed containers, months	3		

CURED PHYSICAL PROPERTIES *

* (Cured 1 hr @ 65°C or 5-7 days @25°C)

	<u>2712-A/B</u>	<u>TEST METHOD</u>
Hardness, Durometer A	32	ASTM-D-2240
Tensile Strength @ 25°C 0.058" thickness, psi	575	ASTM-D-638
Elongation, %	550	ASTM-D-638
Tear, Die C, pli	135	ASTM-D-624

Lap Shear Strength, 5 mil bondline thickness on primed aluminum panels, psi	475	ASTM-D-1002
Outgassing @ 10 ⁻⁶ torr		
TML, %	0.55	ASTM E-595
CVCM, %	0.05	ASTM E-595
Glass transition Temp (Tg), °C	-110	ASTM E-831
Coefficient of thermal expansion, in/in/°C		
alpha 1	54 x 10 ⁻⁶	ASTM E-831
alpha 2	235 x 10 ⁻⁶	ASTM E-831
<u>CURED ELECTRICAL PROPERTIES</u>	<u>2712-A/B</u>	<u>TEST METHOD</u>
Volume resistivity, ohm-cm	1 x 10 ¹⁵	ASTM D-257
Dielectric strength, volts/mil, 0.250" thick	350	ASTM D-149

SAFETY AND FIRST AID

APTEK 2712-A is a silica-filled silicone resin blend that is safe to handle when used properly. It is judged to be low in toxicity and to be rated as a slight skin irritant. Avoid contact with skin and eyes and use in a well-ventilated area and avoid breathing vapors. In case of eye contact, flush with fresh clean water for at least 15 minutes; for skin contact, wash thoroughly with soap and water. If swallowed, drink at least one pint of water and call a physician. Refer to Material Safety Data Sheet for more details.

APTEK 2712-B is a silica-filled silicone resin blend, which is safe to handle when used properly. Avoid skin and eye contact and use in a well-ventilated, hooded area. In case of eye contact, flush profusely with fresh clean water and contact a physician. For skin contact, wash thoroughly with soap and water. If inhaled, move subject to fresh air and provide water to drink. If swallowed, dilute with at least one pint of water and contact physician immediately. Refer to Material Safety Data Sheet for more details.

Revised: 10-17-2011 - di

Issued: 06-17-1998

APTEK[®] is a registered trademark of Aptek Laboratories, Inc.