



APTEK LABORATORIES, INC.

ISO 9001/AS9100 Certified

28570 Livingston Avenue, Valencia, CA 91355-4171 • (661) 257-1677 FAX (661) 257-8939

TECHNICAL DATA & INFORMATION

APTEK® 6521-PMF
Space Grade, High Strength Epoxy ESD Coating/Adhesive

PRODUCT DESCRIPTION

APTEK 6521-PMF is a carbon-filled, thixotropic, one-component, electrically conductive, high strength epoxy coating/adhesive designed to dissipate an electrostatic charge. This low-outgassing system provides high strength over a wide temperature range.

KEY FEATURES AND BENEFITS

- Capable of full cure at RT for application where heat cure is not desired or possible
- Exceeds NASA outgassing requirements for space applications
- Excellent strength properties from -55°C to 175°C
- Excellent reversion resistance for good physical stability under high heat and humidity environments
- Excellent substrate adhesion; superior to silicones

HANDLING INFORMATION

Work life, 5 gm mass, @ 25°C, 50% RH, mins: >30

Notes:

1. Work life will be affected by temperature.
2. **APTEK 6521-PMF** syringes are shipped in dry ice. Upon receipt, transfer frozen syringes to a storage freezer @-60°C or below.
3. To thaw remove from freezer and allow to warm to room temperature. Do not place in oven or microwave-this will shorten use life.
4. Typical thaw time for 3cc syringe @25°C ambient is approximately 10-15 minutes.

- DISCLAIMER NOTICE -

All statements, technical data, and recommendations expressed herein are based on tests believed to be reliable and accurate. However, APTEK LABORATORIES, INC. gives no warranty, expressed or implied, regarding the accuracy of this information. It is intended that the buyer and user of these products shall determine the suitability of the information provided for his specific application, and is responsible for its selection.

APTEK LABORATORIES, INC. shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or misuse of these products, or of the information given in these data bulletins. Purchasers assume all risk and liability whatsoever in connection with the use of these products and this information.

CURE SCHEDULE

5 days at 25°C*
or
1 hour @ 85°C

*Note: For room temperature curing of this adhesive when the material surface is exposed to air during this cure cycle, a blush-type surface appearance can occur. This phenomenon is inherent for this chemistry; however, all physical and electrical properties on bonded parts cured at room temperature are unaffected.

TYPICAL PROPERTIES

(values not to be used for specification purposes)

<u>CHARACTERISTICS</u>	<u>6521-PMF</u>	<u>TEST METHOD</u>
Color	Black	Visual
Specific gravity	1.10	ASTM D-1475
Viscosity @ 20°C, cps	Flowable liquid	ASTM D-1824
Shelf life, @ -60°C or below weeks in factory sealed containers	4	
<u>CURED PHYSICAL PROPERTIES</u>	<u>6521-PMF</u>	<u>TEST METHOD</u>
Lap Shear, primed Al to primed Al, psi	3500	SCGMS51116, Rev. A
Outgassing @ 10 ⁻⁶ Torr TML, % CVCM, % *after WVR subtracted	0.60* 0.004	ASTM-E595 ASTM-E595
<u>CURED ELECTRICAL PROPERTIES</u>	<u>6521-PMF</u>	<u>TEST METHOD</u>
Electrical Resistance @ 25°C, 5 mil thick film, ohms	5 x 10 ⁵	SCGMS51116, Rev. A

SAFETY AND FIRST AID

APTEK 6521-PMF is safe to handle when used properly. Avoid contact with skin and eyes and use in a well-ventilated area and avoid breathing vapors. In case of eye contact, flush with fresh clean water for at least 20 minutes. For skin contact, wash thoroughly with soap and water. If swallowed, do not induce vomiting, drink at least one pint of water and call a physician. Refer to Material Safety Data Sheet for more details.

Revised: 08/17/20 – mjv

APTEK® is a registered trademark of Aptek Laboratories, Inc.