

APTEK LABORATORIES, INC.

ISO 9001 / AS9100 Certified

28570 Livingston Avenue, Valencia, CA 91355-4171 • (661) 257-1677 FAX (661) 257-8939

TECHNICAL DATA & INFORMATION

APTEK[®] 2214LV-A/B

Space Grade, Low Modulus Urethane ESD Coating

PRODUCT DESCRIPTION

APTEK 2214LV-A/B is a carbon-filled, thixotropic, two component, electrically conductive, flexible urethane coating/adhesive designed to dissipate an electrostatic charge. This low-outgassing system provides a combination of high flexibility and good tensile strength/elongation characteristics.

APTEK 2214LV-A/B is a low viscosity version of standard APTEK 2214-A/B designed for spray or brush applications.

KEY FEATURES AND BENEFITS

- · Capable of full cure at RT for application where heat cure is not desired or possible
- · Exceeds NASA outgassing requirements for space applications
- Non-TDI based for safety
- Excellent reversion resistance for good physical stability under high heat and humidity environments
- Tg BELOW -60°C for excellent low temperature cycling, storage and performance
- · Excellent substrate adhesion; superior to silicones
- · Available in pre-measured kits to minimize handling

HANDLING INFORMATION

Mix ratio, parts by weight: 100 (2214LV-A) / 5 (2214LV-B)

Work life, 50 gm mass, @ 25°C, 50% RH, mins: >60

Note: Work life will be affected by temperature, humidity, and degree of solvent evaporation.

Handling Notes:

- To reduce mixed viscosity, dilute A/B mixture with reagent grade toluene as needed.

- APTEK 2214LV-B should be stored in tightly closed, factory sealed containers at a temperature of 20-30°C. Crystallization, cloudiness, or formation of an insoluble white precipitate which is the solid dimer of the liquid Part B may occur upon prolonged storage at temperatures below 20°C. The precipitate is not harmful; however, do not shake the bottle. Decant clear liquid out of bottle without disturbing the precipitate.

- Use entire bottle of Part B for each application if possible. Unused portion must be blanketed with dry nitrogen or argon and resealed to avoid moisture contamination.

- DISCLAIMER NOTICE -

All statements, technical data, and recommendations expressed herein are based on tests believed to be reliable and accurate. However, APTEK LABORATORIES, INC. gives no warranty, expressed or implied, regarding the accuracy of this information. It is intended that the buyer and user of these products shall determine the suitability of the information provided for his specific application, and is responsible for its selection.

APTEK LABORATORIES, INC. shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or misuse of these products, or of the information given in these data bulletins. Purchasers assume all risk and liability whatsoever in connection with the use of these products and this information.

MIXING

Weigh 100 parts of APTEK 2214LV Part A into a clean dry glass, metal, or plastic container and then add 5 parts of APTEK 2214LV Part B. Machine mix on slow speed or hand stir with glass or metal stirrer until complete and thorough blending is achieved. Care should be taken to avoid any source of moisture contamination or air entrapment during mix.

Note:

@ 100 V Bias

For best results and a bubble-free coating, briefly vacuum mixture at less than 10 mm Hg. As soon as bubbles appear at the surface, shut off vacuum immediately. If not, material will boil violently and splash within vacuum chamber.

CURE SCHEDULE

2 hrs @ RT + 2 hrs @ 100°C

* NOTE: After 24 hours at 25° C, a 5 mil film is cured enough to handle without being tacky. The surface resistivity will be approximately 5 x 10^{6} ohms per square. Allow the full 7 day cure to achieve ultimate physical properties and meet the NASA outgassing requirements.

TYPICAL PROPERTIES

(values not to be used for specification purposes)

| CHARACTERISTICS | <u>2214LV-A</u> | <u>2214LV-B</u> | TEST METHOD |
|---|-----------------|-----------------|-------------|
| Color | Black | Pale yellow | Visual |
| Specific gravity | 0.92 | 1.01 | ASTM D-1475 |
| Viscosity @ 20°C, cps | 100 est. | 10 | ASTM D-1824 |
| Flash point, °C | 7 | 7 | ASTM D-92 |
| Shelf life @ 25°C, months factory sealed containers | 6 | 6 | |

Notes: Shelf life may be reduced once containers are opened and material is exposed to air and moisture. To preserve maximum use life, blanket the contents of the containers with dry nitrogen or argon before resealing.

| CURED PHYSICAL PROPERTIES | <u>2214LV-A/B</u> | TEST METHOD |
|--|-----------------------------------|---------------------------------|
| Hardness, Durometer A | 70 | ASTM D-2240 |
| Glass transition temp., °C | <-60 | Perkin Elmer TS-2 |
| Outgassing @ 10 ⁻⁶ Torr TML, % CVCM, % | 0.59 0.04 | ASTM-E-595 ASTM-E-595 |
| Fungus resistance CURED ELECTRICAL PROPERTIES | non-nutrient 2214LV-A/B | ASTM-G-21 <u>TEST METHOD</u> |
| Surface resistivity @ 25°C, 5 mil thick film, ohms/square | 10 ⁶ - 10 ⁹ | QCP-016-0110 |

SAFETY AND FIRST AID

APTEK 2214LV-A is a carbon-filled polyol resin containing solvent and is thus considered a flammable liquid and should be treated with caution. Avoid storage temperatures above 35°C and keep away from flame, sparks, or other sources of ignition. Use in well- ventilated area and avoid breathing vapors. In case of eye contact, flush with fresh clean water for at least 15 minutes; for skin contact, wash thoroughly with soap and water. If swallowed, drink at least one pint of water and call a physician. Refer to Material Safety Data Sheet for more details.

APTEK 2214LV-B is an organic isocyanate containing solvent and is thus considered a flammable liquid and should be treated with caution. Avoid storage temperatures above 35°C and keep away from flame, sparks, or other sources of ignition. Use in well-ventilated area and avoid breathing vapors. Inhalation of vapors may result in breathlessness, severe coughing, chest discomfort, and irritation of mucous membranes. Avoid skin and eye contact and use in a well-ventilated, hooded area. In case of eye contact, flush profusely with fresh clean water and contact a physician. For skin contact, wash thoroughly with soap and water. If inhaled, move subject to fresh air and provide water to drink. If swallowed, dilute with at least one pint water and contact physician immediately. Refer to Material Safety Data Sheet for more details.

Revised: 10/11/21 – jmv **APTEK**[®] is a registered trademark of Aptek Laboratories, Inc.